



# Technical Data Sheet

## SCM COAT-SE100 (Pure)

*Expert Manufacturer*  
*Best Partner for You*  
**+82-70-7739-6268**

### Description

**SCM COAT-SE100** was developed for excellent high elongation mechanical properties.  
**SCM COAT-SE100** is two component high quality polyurea zero VOC's (Volatile Organic Compound) and 100% solid content material. (It can be supplied for strong resistance to UV with special additive)

### Use

For waterproofing.  
Area requiring high elongation properties.

### Features

Zero VOC's (100% solid).  
Fast curing time (30sec).  
High elongation.  
Able to cure at -25°C.  
Excellent resistance to crack.

### Packing

**SCM COAT-SE100** "A" & "B" is available in 200L steel drums.

## *Physical Properties*

### Wet properties

Appearance	liquid
Specific gravity (25°C)	"A" 1.09±0.1 "B" 1.00±0.1
Viscosity(cps)	"A" 600±100 "B" 500±100
Thermal stability	0°C to 50°C
Shelf life(10-40°C) (Unopened containers)	12 months

### Process properties

Gel time	5sec
Tack free time	10sec
Recoat	0-12hr

***Good to Great***

# Technical Data Sheet

## SCM COAT-SE100 (Pure)

*Expert Manufacturer*  
*Best Partner for You*  
**+82-70-7739-6268**

### Dry properties

Tensile strength ASTM D 412	15±4 Mpa
Elongation	600±100%
Hardness (Shore)	70-75 (A)
Tear strength	55±5 N/mm
Abrasion resistance (1kg ,1000rev)	650mg(CS-17)
Impact resistance (Thickness 1mm)	2.5Mpa

### Chemical resistance

10%-Sulfuric acid	Not change
30%-Sodiumchloride	Not change
30%-Sodium hydroxide	Not change
50%- Sodium hydroxide	Not change
Diesel	Not change
Salt water resistance	Not change

### Others

#### Caution

Store in warm place preventing from freezing.  
Contents should not be exposed for a long time .  
In case of contact with skin and eyes ,flush immediately with plenty of water and seek medical advice.  
For further information , see the Material Safety Data Sheet.



# Technical Data Sheet

## SCM COAT-SE100 (Pure)

*Expert Manufacturer*  
*Best Partner for You*  
**+82-70-7739-6268**

### Coverage rates

Thickness	Requirement
1 mm	1.0kg/ m <sup>2</sup>
2 mm	2.0kg/ m <sup>2</sup>
3 mm	3.0kg/ m <sup>2</sup>
Without any loss	

### Application

Mix ratio 1:1 , It must use spraying equipment for polyurea such as Graco's Reactor, Glass Craft or other equivalent machine. And keep the pressure minimum 1500psi with heating to 65–70 °C. Component "B" must be mixing for 1 hour before spraying , and while spraying.

### Surface preparation

**Concrete** Concrete should be allowed to cure a minimum of 28 days. The surface of a concrete subfloor should be dry such as moisture content below 8%, It should also be blasting to remove all laitance and expose all voids.

And filling below hole with high quality filler such as mortar ,epoxy.

**Metal** All the processes should be based on the Specification. If no provisions are in the Specification, the following basic methods and SSPC and should be consulted to prepare a surface.

Rusts, dusts, and other contaminants on the surface should be completely eliminated according to the instructions of the supervisor. The surface should be fully dried before coating.

### Color

Clear/Neutral. Custom colors are available upon.

### Clean up

Cleaning of Tools Clean all tools and application equipment with Thinner (Diesel oil ,DOP , Ethyle cellosolve) immediately after use. Cured material can only be removed mechanically.

[Contact our R&D center if you need more informations](#)

**Good to Great**